OMPAÑIA ESPAÑOLA DE LAMINACION, S.L.
FICINAS: c/Ferralla,12 Pol.Ind. "SAN VICENTE"
3755 Castellbisbal (BARCELONA)
IF: B-59/559351 Sociedad Unipersonal
eléfono: +34 93 773 04 00 - Fax: +34 93 772 02 76
alidad: +34 93 817 66 84 - Fax: +34 93 773 05 52

CELSA GROUP™ | CELSA BARCELONA

Sostenibilidad Siderúrgica Gestión RSE SGSS-001/2010

CE 0099 06 CELSA01BCN

MILL INSPECTION CERTIFICATE
EN 10.204:2004, Type 3.1.

tandard: EN 10025-1,2/2004
ype: S 355 JO +AR
t. Mea.: EN 10365/2017
t. Tol.: EN 10279/2000
ur Ref: 02795365
(B26-31BAL2)

Customer: AJN STEELSTOCK LTD
ICKNEILD WAY, KENTFORD, SUFFOLK
CB8 7QT NEWMARKET
United Kingdom

Destination: AJN STEELSTOCK LTD
ICKNEILD WAY, KENTFORD, SUFFOLK
CB8 7QT NEWMARKET
United Kingdom

Document n°: 201510920
Order number : 10569593
Your order : 68863

Material (L=Lenght)	Heat Number	CHEMICAL ANALYSIS															MECHANICAL PROPERTIES		
		C	Mn	Si	S	P	Cr	Ni	Cu	Mo	V	Nb	AL	N	Ti	CEV	Yield Str.	Tensile Str.	Elong. L0= 5,65VSo
		%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	MPA	MPA	%
S 355 JO +AR PFC150X90 L.8.0 m	CE215626	0.090	1.150	0.180	0.015	0.023	0.110	0.120	0.360	0.020	0.028	0.001	0.003	0.0116	0.001	0.345	392	522	31.1
S 355 JO +AR PFC150X90 L.8.0 m	CE215627	0.090	1.160	0.180	0.017	0.024	0.110	0.110	0.350	0.020	0.028	0.001	0.003	0.0104	0.001	0.346	397	527	31.2
S355JO +AR PFC150X90 L.12.2m	CE215628	0.080	1.140	0.180	0.019	0.025	0.150	0.120	0.370	0.020	0.028	0.001	0.003	0.0097	0.001	0.342	398	528	31.6
S 355 JO +AR PFC150X90 L.8.0 m	CE215628	0.080	1.140	0.180	0.019	0.025	0.150	0.120	0.370	0.020	0.028	0.001	0.003	0.0097	0.001	0.342	398	528	31.6
S 355 JO +AR PFC150X90 L.8.0 m	CE215629	0.080	1.170	0.190	0.015	0.022	0.160	0.110	0.360	0.019	0.029	0.002	0.003	0.0117	0.001	0.348	394	524	32.6
S355JO +AR PFC180X90 L.12.2m	CE215674	0.090	1.120	0.170	0.014	0.030	0.210	0.140	0.390	0.025	0.029	0.001	0.002	0.0088	0.001	0.365	381	524	28.8
S355JO +AR PFC180X90 L.6.1m	CE215674	0.090	1.120	0.170	0.014	0.030	0.210	0.140	0.390	0.025	0.029	0.001	0.002	0.0088	0.001	0.365	381	524	28.8
S355JO +AR PFC180X90 L.8.0 m	CE215674	0.090	1.120	0.170	0.014	0.030	0.210	0.140	0.390	0.025	0.029	0.001	0.002	0.0088	0.001	0.365	381	524	28.8
S 355 JO +AR PFC180X90 L.9.5 m	CE215674	0.090	1.120	0.170	0.014	0.030	0.210	0.140	0.390	0.025	0.029	0.001	0.002	0.0088	0.001	0.365	381	524	28.8
S355JO +AR PFC180X90 L.12.2m	CE215675	0.090	1.160	0.200	0.015	0.030	0.140	0.120	0.360	0.020	0.029	0.001	0.003	0.0120	0.001	0.353	381	524	29.0
S355JO +AR PFC180X90 L.6.1m	CE215675	0.090	1.160	0.200	0.015	0.030	0.140	0.120	0.360	0.020	0.029	0.001	0.003	0.0120	0.001	0.353	381	524	29.0
S355JO +AR PFC180X90 L.6.1m	CE215684	0.100	1.150	0.170	0.014	0.017	0.090	0.110	0.360	0.018	0.029	0.001	0.002	0.0102	0.001	0.350	416	542	26.9

Product suitable for galvanizing: 0.14<=Si<=0.25 & P<=0.035.
Intended use: construction and civil engineering.
Durability: not determined.
Regulated substances: not determined

291680

Castellbisbal,22.05.2018
Juan Diego Martínez Gálvez
Quality Control Manager

COMPAÑIA ESPAÑOLA DE LAMINACION, S.L. CELSA CASTELLBISBAL

Hot rolled products of structural steels.
Steel making: Electric arc melting and rolled process.
We hereby certify that the delivered material complies with the terms of the order.

Despatch No.: 1007999 S/O No.: 2285.02 Cust Name: Weldrite Structures Ltd
Cust Ref: WSL9946/C1255/L3 Parent: 291680 Weight: Pieces: 16 Size: 12.200
Message: AJN Steelstock Ltd Product: CH18090 Child Batch No: 291680

OMPAÑIA ESPAÑOLA DE LAMINACION, S.L.
FICINAS: c/Ferralla,12 Pol.Ind. "SAN VICENTE"
3755 Castellbisbal (BARCELONA)
IF: B-59/559351 Sociedad Unipersonal
eléfono: +34 93 773 04 00 - Fax: +34 93 772 02 76
alidad: +34 93 817 66 84 - Fax: +34 93 773 05 52

CELSA GROUP™ | CELSA BARCELONA

Sostenibilidad Siderúrgica Gestión RSE SGSS - 001/2010

CE 0099
06
CELSA01BCN

MILL INSPECTION CERTIFICATE
EN 10.204:2004, Type 3.1.

tandard: EN 10025-1,2/2004
ype: S 355 JO +AR
t. Mea.: EN 10365/2017
t. Tol.: EN 10279/2000
ur Ref: 02795365
(B26-31BRESI)

Customer: AJN STEELSTOCK LTD
ICKNEILD WAY, KENTFORD, SUFFOLK
CB8 7QT NEWMARKET
United Kingdom

Destination: AJN STEELSTOCK LTD
ICKNEILD WAY, KENTFORD, SUFFOLK
CB8 7QT NEWMARKET
United Kingdom

Document n°: 201510920
Order number : 10569593
Your order : 68863

Material (L=Lenght)	Heat Number	MECH. PROPERTIES Impact Test 1 J	Impact Test 2 J	Impact Test 3 J	Imp. Test Avg. J	Tp Imp. Test °C
S 355 JO +AR PFC150X90 L.8.0 m	CE215626	137	107	113	119	0
S 355 JO +AR PFC150X90 L.8.0 m	CE215627	137	107	113	119	0
S355JO +AR PFC150X90 L.12.2m	CE215628	135	104	110	116	0
S 355 JO +AR PFC150X90 L.8.0 m	CE215628	135	104	110	116	0
S 355 JO +AR PFC150X90 L.8.0 m	CE215629	139	109	115	121	0
S355JO +AR PFC180X90 L.12.2m	CE215674	148	118	124	130	0
S355JO +AR PFC180X90 L.6.1m	CE215674	148	118	124	130	0
S355JO +AR PFC180X90 L.8.0 m	CE215674	148	118	124	130	0
S 355 JO +AR PFC180X90 L.9.5 m	CE215674	148	118	124	130	0
S355JO +AR PFC180X90 L.12.2m	CE215675	148	118	124	130	0
S355JO +AR PFC180X90 L.6.1m	CE215675	148	118	124	130	0
S355JO +AR PFC180X90 L.6.1m	CE215684	139	107	114	120	0

ype sample for Impact Test: Direct or transformed data to KV 550/10.

291680

Castellbisbal,22.05.2018
Juan Diego Martínez Gálvez
Quality Control Manager

COMPAÑIA ESPAÑOLA DE LAMINACION, S.L. CELSA CASTELLBISBAL